

PROPERTY	TYPICAL VALUE	
Flexural Strength (PSI)	13.5 X 10 ³	ASTM D 790
Flexural Modulus (PSI)	1.4 X 10 ⁶	ASTM D 790
Tensile Strength (PSI)	9 X 10 ³	ASTM D 638
Tensile Modulus (PSI)	1.1 X 10 ⁶	ASTM D 638
Impact Strength (IZOD) (ft. lbs./in. notched)	8	ASTM D 256
Barcol Hardness	55	ASTM D 2583
Thermal Coefficient of Linear Expansion (in./in./°F)	1.7 X 10 ⁻⁵	ASTM D 696
Water Absorption	.4	ASTM D 570
Specific Gravity	1.83	ASTM D 792